sappi | Raw



Raw Product Information



Raw is a coated fine paper available in sheets and reels for offset printing.

Technical specifications

Parameter	Standard	Unit							
Basis weight	ISO 536	g/m²	115	135	150	170	200	250	300
Brightness (illuminant D65/10°)	ISO 2470-2	%	104	104	104	104	104	104	104
CIE whiteness (D65/10°)	ISO 11475	%	144	144	144	144	144	144	144
Opacity	ISO 2471	%	96	97	98	99	>99	>99	>99
Roughness Bendtsen	ISO 8791-2	ml/min	< 450	< 450	< 450	< 450	< 450	< 500	< 550
Thickness	ISO 534	μm	138	162	180	204	240	300	360
Bulk	ISO 534	cm³/g	1.20	1.20	1.20	1.20	1.20	1.20	1,20
Relative humidity (23°C)	TAPPI 502	%	50	50	50	50	50	50	50

Mill Certification



The environmental performance is monitored and continuously improved according to the requirements of Eco-Management and Audit Scheme (EMAS).



The quality of the manufacturing is managed according to the requirements of ISO 9001



The environmental aspects of the mill are managed according to the requirements of ISO 14001.



The energy consumed and the emissions generated by the mill are managed according to ISO 50001.



All fibers from sustainability and controlled sources. FSC® may have limited availability, please check with your local sales office.



All fibers from sustainability and controlled sources. PEFCTM may have limited availability, please check with your local sales office.



The health and safety of the mill employees are managed according to the requirements of ISO 45 001.

Product Certification



All fibers from sustainable and controlled sources. PEFC may have limited availability, please check with your local sales office.



All fibers from sustainable and controlled sources. FSC may have limited availability, please check with your local sales office.



Archivability tested according to the requirements of DIN 6738, Lifespan class - LDK 6-70.



Pulp is bleached without the use of chlorine (ECF).



Dry toner: Suitable for dry toner.